

® = registered Trademark of BASF SE

Irganox[®] MD 1024

Metal deactivator and antioxidant for wire and cable applications

Characterization


Chemical name

Irganox MD 1024 is a metal deactivator and primary (phenolic) antioxidant
2',3-Bis[[[3-[3,5-di-tert.-butyl-4-hydroxyphenyl]propionyl]]propionohydrazide

CAS number

32687-78-8

Chemical formula



Molecular weight

553 g/mol

Applications

- Polyethylene wire and cable resins
- Filled polyolefins
- Polyolefins in contact with copper NBR fuel hoses
- X-SBR
- SBR
- Styrene homo- and copolymers

Features/benefits

As the world's most widely applied metal deactivator for telecommunications wire and cable, Irganox MD 1024 provides unmatched extraction resistance and processing stabilization. Used alone, or with other phenolic antioxidants, such as Irganox 1010, Irganox MD 1024 is recommended for the stabilization of polymers in contact with copper both during processing and long-term service.

Product forms

Irganox MD 1024 white to slightly yellowish crystalline powder

Guidelines for use

For any application in contact with copper during processing or long-term service: 0.1 % – 0.2 % Irganox MD 1024.

Physical properties

Melting range	221–232 °C
Flashpoint	> 180 °C
Specific gravity (20 °C)	1.11 g/ml
Vapor pressure (20 °C)	approx. 1 E-10 Pa

Bulk density	
Powder	320–380 g/l

Solubility (20 °C)	g/100 g solution
Acetone	4
Benzene	0.1
Chloroform	0.4
Hexane	<0.01
Methanol	4
Water	<0.01

Health & Safety

Irganox MD 1024 exhibits a very low order of oral toxicity and does not present any abnormal problems in its handling or general use.

Detailed information on handling and any precautions to be observed in the use of the product(s) described in this leaflet can be found in our relevant health and safety information sheet.

Note

The descriptions, designs, data and information contained herein are presented in good faith, and are based on BASF's current knowledge and experience. They are provided for guidance only, and do not constitute the agreed contractual quality of the product or a part of BASF's terms and conditions of sale. Because many factors may affect processing or application/use of the product, BASF recommends that the reader carry out its own investigations and tests to determine the suitability of a product for its particular purpose prior to use. It is the responsibility of the recipient of product to ensure that any proprietary rights and existing laws and legislation are observed. No warranties of any kind, either expressed or implied, including, but not limited to, warranties of merchantability or fitness for a particular purpose, are made regarding products described or designs, data or information set forth herein, or that the products, descriptions, designs, data or information may be used without infringing the intellectual property rights of others. Any descriptions, designs, data and information given in this publication may change without prior information. The descriptions, designs, data and information furnished by BASF hereunder are given gratis and BASF assumes no obligation or liability for the descriptions, designs, data or information given or results obtained, all such being given and accepted at the reader's risk.

September 2010