



Ciba


Ciba® TINUVIN® 328

Light Stabiliser

General

TINUVIN 328 is a UV absorber of the hydroxyphenylbenzotriazole class designed for coatings. Because of its extended UV absorption, TINUVIN 328 provides efficient protection to coatings and light sensitive substrates.

Chemical Composition




2-(2H-benzotriazol-2-yl)-4,6-ditertpentylphenol

Molecular weight: 351.5

CAS No. 25973-55-1

Transmittance Spectrum (in Toluene, cell thickness 1 cm)



Explanation: Top line: 0.001 % TINUVIN 328, corresponds to 0.25 % in a 40 µm film
 Second line: 0.002 % TINUVIN 328, corresponds to 0.5 % in a 40 µm film
 Third line: 0.004 % TINUVIN 328, corresponds to 1.0 % in a 40 µm film
 Bottom line: 0.006 % TINUVIN 328, corresponds to 1.5 % in a 40 µm film



Ciba® TINUVIN® 328

Light Stabiliser

Physical Properties

Appearance: slightly yellow powder

Melting range: 80-88°C

Solubility at 20°C (g/100 g solution):

butylcarbitol	3.5
butanol	2.5
butylacetate	15
ethylglycol	4
1-methoxypropylacetate-2	10
methylethylketone	14
Solvesso 100 ¹⁾	25
Solvesso 150 ¹⁾	25
xylene	34
water	< 0.01

¹⁾ Trade Mark of Esso

Application

TINUVIN 328 is recommended for applications such as:

- automotive coatings
- industrial coatings
- trade sale paints such as wood stains or do-it-yourself paints.

TINUVIN 328 may be used in combination with a light stabilizer of the sterically hindered amine or aminoether class (HALS) such as recommended below. These combinations give coatings superior protection against gloss reduction, cracking, blistering, delamination and color change. TINUVIN 328 is only recommended for ambient and low temperature cured systems, i.e. air drying alkyd based systems.

The amount of TINUVIN 328 required for optimum performance should be determined in trials covering a concentration range.

Recommended concentrations :

(concentrations are based on weight percent binder solids)

1 - 3 % TINUVIN 328
+
0.5 - 2 % TINUVIN 144, TINUVIN 292, or TINUVIN 123

Safety and Handling

TINUVIN 328 should be handled in accordance with good industrial practice. Detailed information is provided in the Safety Data Sheet.

Ciba Specialty Chemicals

Coating Effects Segment



Ciba[®] TINUVIN[®] 328

Light Stabiliser

Important Notice

Purchase of TINUVIN 328 alone does not permit use in combination with hindered amine lightstabilizers (HALS) in stoving lacquers covered by US Patent Nos. 4'314'933, 4'426'471, 4'426'472, 4'344'876 and EP Patent No. 52073 and patent applications in other countries.

IMPORTANT: The following supersedes Buyer's documents. SELLER MAKES NO REPRESENTATION OR WARRANTY, EXPRESS OR IMPLIED, INCLUDING OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. No statements herein are to be construed as inducements to infringe any relevant patent. Under no circumstances shall Seller be liable for incidental, consequential or indirect damages for alleged negligence, breach of warranty, strict liability, tort or contract arising in connection with the product(s). Buyer's sole remedy and Seller's sole liability for any claims shall be Buyer's purchase price. Data and results are based on controlled or lab work and must be confirmed by Buyer by testing for its intended conditions of use. The product(s) has not been tested for, and is therefore not recommended for, uses for which prolonged contact with mucous membranes, abraded skin, or blood is intended; or for uses for which implantation within the human body is intended.